

(19)



Europäisches Patentamt

European Patent Office

Office européen des brevets



(11)

EP 1 127 959 A1

(12)

## EUROPEAN PATENT APPLICATION

(43) Date of publication:

29.08.2001 Bulletin 2001/35

(51) Int Cl.7: C23C 28/00, C23C 4/02

(21) Application number: 01102982.4

(22) Date of filing: 08.02.2001

(84) Designated Contracting States:

AT BE CH CY DE DK ES FI FR GB GR IE IT LI LU  
MC NL PT SE TR

Designated Extension States:

AL LT LV MK RO SI

(30) Priority: 23.02.2000 US 511857

(71) Applicant: Howmet Research Corporation

Whitehall, Michigan 49461 (US)

(72) Inventors:

- Warnes, Bruce M.  
Muskegon, Michigan 49445 (US)
- Cockerill, Joel Lee  
Montague, Michigan 49437 (US)
- Schilbe, John Edward  
Whitehall, Michigan 49461 (US)

(74) Representative: Hoeger, Stellrecht &amp; Partner

Uhlandstrasse 14 c  
70182 Stuttgart (DE)

## (54) Thermal barrier coating method and article

(57) An outwardly grown diffusion aluminide bondcoat is formed on a superalloy substrate and has higher concentrations of Al and Pt and lower concentrations of harmful impurities (e.g. Mo, W, Cr, Ta, S, etc.) at an outermost region of the bondcoat than at an innermost region thereof adjacent the substrate. The bondcoat is

pretreated prior to deposition of a ceramic thermal insulative layer in a manner that reduces grain boundary ridges on the outermost bondcoat surface without adversely affecting the outermost region thereof, and then is heat treated to thermally grow a stable alpha alumina layer on the bondcoat prior to deposition of a ceramic layer.




FIG. 1

EP 1 127 959 A1

**Description****FIELD OF THE INVENTION**

- 5 [0001] The present invention relates to thermal barrier coatings for components, such as gas turbine engine blades and vanes, wherein the thermal barrier coating exhibits improved coating life.

**BACKGROUND OF THE INVENTION**

- 10 [0002] Advancements in propulsion technologies have required gas turbine engines to operate at higher temperatures. This increase in operating temperature has required concomitant advancements in the operating temperatures of metal (e.g. superalloy) turbine engine components. Thermal barrier coatings have been used to meet these higher temperature requirements. Typical thermal barrier coatings comprise alumina and/or zirconia based ceramic which provide a thermal insulative layer to protect the metal component from the high temperatures.
- 15 [0003] Thermal barrier coatings have been applied to metal components by first coating the component with a bondcoat, which may comprise an inwardly or outwardly grown platinum modified diffusion aluminide bondcoat and/or MCrAlY overlay bondcoat where M is Ni and/or Co. After applying the bondcoat, the coated component typically is grit blasted and vacuum heat treated, or vice versa, to promote the formation of a thermally grown oxide (TGO) layer typically comprising alumina on the aluminum-rich underlying bondcoat. The component then is coated by electron beam physical vapor deposition with a thermal insulative layer of alumina, zirconia, or other ceramic material. For example, U.S. Patents 5 716 720 and 5 856 027 describe a thermal barrier coating system comprising a clean platinum modified diffusion aluminide bondcoat on the substrate, a thermal grown alumina layer, and a thermal insulative ceramic layer on the alumina layer. The platinum modified diffusion aluminide bondcoat comprises an outwardly grown diffusion aluminide coating produced by CVD (chemical vapor deposition) processing using high substrate temperature and low activity coating gases that produce higher concentrations of Pt and Al and low concentrations of harmful refractory metal impurities (e.g. Mo, W, Cr, Ta, etc.) and surface active impurities (e.g. S, P, Cl, B, etc.) at the outermost zone or region of the aluminide coating.
- 20 [0004] The life of a thermal barrier coating; i.e. time to coating spallation, is known to be related to the surface characteristics of the bondcoat and the particular phase of the thermally grown alumina present between the insulative layer and the bondcoat. Negative effects of bondcoat surface roughness on coating life have been reported by Jordan in "Bondcoat Strength and Stress Measurements in Thermal Barrier Coatings", US Department of Energy Report (subcontract # 95-01-SR030), September 30, 1997, where it was reported that platinum aluminide bondcoat surfaces include grain boundary ridges that act as sites for stress concentration and damage accumulation during thermal cycling of thermal barrier coated substrates. Grain boundary ridges act as sites for preferential oxidation, void formation, and crack initiation which result in the thermally grown alumina spalling prematurely.
- 25 [0005] The formation of the thermally grown alumina layer on the aluminum-rich bondcoat involves several metastable transition phases, such as a cubic gamma alumina phase transforming to a tetragonal delta alumina phase then to a monoclinic theta alumina phase finally to a rhombohedral alpha alumina phase, the formation of which occurs by heterogeneous nucleation and growth of the alpha phase from the monoclinic theta phase. The sum of the metastable transitions involves a substantial molar volume reduction of approximately 9%, a significant portion of which is attributable to the final transition from the theta phase to alpha phase.
- 30 [0006] An object of the present invention is to provide a method of pretreating a superalloy or other substrate prior to coating with a thermal insulative layer of a thermal barrier coating system in a manner to reduce adverse effects of bondcoat surface roughness on life of the thermal barrier coating.
- 35 [0007] Another object of the present invention is to provide a method of pretreating a superalloy or other substrate prior to coating with a thermal insulative layer of a thermal barrier coating system in a manner to reduce adverse effects of metastable phases of thermally grown alumina on life of the thermal barrier coating.
- 40 [0008] A still further object of the present invention is to significantly increase the life of the thermal barrier coating system under high temperature cyclic oxidation conditions.
- 45
- 50

**SUMMARY OF THE INVENTION**

- 55 [0009] The present invention involves forming on a superalloy or other metallic substrate an outwardly grown diffusion aluminide bondcoat that has higher concentrations of Al and optionally Pt and lower concentration of a harmful refractory metal impurity (e.g. Mo, W, Cr, Ta, etc.) at an outermost zone or region of the bondcoat than at an innermost zone or region thereof and pretreating the bondcoat by repetitively moving the bondcoated substrate in contact with abrasive media in a container to reduce bondcoat grain boundary ridges, while leaving at least a portion, preferably all, of the outermost Al-rich zone or region of the original Al-rich bondcoat. The repetitive moving can be achieved by media bowl

polishing.

[0010] The present invention also involves heat treating the pretreated bondcoated substrate under temperature and time conditions in air to form a stable alpha alumina layer on the bondcoat prior to deposition of the ceramic thermal insulative layer.

[0011] A thermal barrier coating system formed pursuant the present invention exhibits a significant increase in coating life (time to coating spallation) in cyclic oxidation tests at elevated temperatures.

[0012] The above objects and advantages of the present invention will become more readily apparent from the following description taken with the following drawings.

## DESCRIPTION OF THE DRAWINGS

[0013] Figure 1 is a graph of concentrations, in weight %, of Pt, Al, Cr, W, Ta, and Mo across the thickness of a platinum modified diffusion aluminide bondcoat with 0 thickness being the outer surface of the bondcoat.

[0014] Figure 2 is a bar graph of average cycles to failure of thermal barrier coating systems wherein the bondcoat was pretreated by vapor honing, grit blasting and media bowl polishing pursuant to the invention.

[0015] Figure 3 is a graph of average cycles to failure of thermal barrier coating systems wherein the bondcoat was pretreated by media bowl polishing for different times.

[0016] Figure 4A is a photomicrograph of a Pt modified diffusion aluminide coating before media polishing, Figure 4B is a photomicrograph of the Pt modified diffusion aluminide coating after media polishing for 10 minutes, and Figure 4C is a photomicrograph of the Pt modified diffusion aluminide coating after media polishing for 30 minutes.

[0017] Figure 5A is a photomicrograph of a Pt modified diffusion aluminide coating after vapor honing at 20 psi, and Figure 5B is a photomicrograph of the Pt modified diffusion aluminide coating after vapor honing at 60 psi.

[0018] Figure 6A is a photomicrograph of a Pt modified diffusion aluminide coating after grit blasting at 20 psi, and Figure 6B is a photomicrograph of the Pt modified diffusion aluminide coating after grit blasting at 40 psi.

[0019] Figure 7 is a time-temperature-transition diagram for alpha alumina formation on an untreated (unworked) outwardly grown platinum modified diffusion aluminide.

[0020] Figure 8 is a graph of air oxidation time (transformation finish time) needed to form stable alpha alumina in air at 1975 degrees F versus the time of media bowl polishing.

## DESCRIPTION OF THE INVENTION

[0021] An exemplary embodiment of the present invention involves forming on a superalloy or other metallic substrate an outwardly grown platinum modified diffusion aluminide bondcoat that has higher concentrations of Al and Pt and lower concentrations of harmful refractory metal impurities (e.g. Mo, W, Cr, Ta, etc.) at an outermost zone or region of the bondcoat than at an innermost zone or region thereof and pretreating the bondcoated substrate in a manner that reduces bondcoat grain boundary ridges, and then to form a stable alpha alumina layer on the bondcoat prior to deposition of the thermal insulative layer in a manner that significantly increases coating life.

[0022] The substrate can comprise nickel and cobalt superalloy and other metallic substrates which may comprise equiaxed, directionally solidified and single crystal castings as well as other forms of these materials, such as forgings, pressed powder components, machined components, and other forms. For example only, the substrate may comprise the well known Rene' N5 nickel base superalloy having a composition of Ni-7.0% Cr-6.2% Al-7.5% Co-6.5% Ta-1.5% Mo-5.0% W-3.0% Re-0.15% Hf-0.05% C-0.018% Y (where % is in weight %) used for making single crystal turbine blades and vanes. Other nickel base superalloys which can be used include, but are not limited to, MarM247, CMSX-4, PWA 1422, PWA 1480, PWA 1484, Rene' 80, Rene' 142, and SC 180. Cobalt based superalloys which can be used include, but are not limited to, FSX-414, X-40, MarM509 and others.

[0023] The bondcoat preferably comprises an outwardly grown platinum modified diffusion aluminide bondcoat that has higher concentrations of Al and Pt and lower concentrations of harmful refractory metal impurities (e.g. Mo, W, Cr, Ta, etc.) at the outermost zone or region of the bondcoat than at the innermost zone or region thereof. The outwardly grown platinum modified diffusion aluminide bondcoat is formed by first electroplating a platinum layer on the substrate using an alkali or alkaline earth hydroxide platinum plating solution as described in U.S. Patent 5 788 823, the teachings of which are incorporated herein by reference. The platinum coated substrate then is subjected to a chemical vapor deposition (CVD) process described in U.S. Patents 5 658 614 and 5 989 733, the teachings of which are incorporated herein by reference. The CVD process described in the these patents uses an aluminum trichloride coating gas in a hydrogen carrier gas at a substrate coating temperature of at least 1832 degrees F to form the outwardly grown platinum modified diffusion aluminide bondcoat. The bondcoat comprises an innermost diffusion zone or region adjacent the substrate and an outermost additive layer zone or region formed by outward diffusion of nickel from the substrate and its subsequent reaction with aluminum from the coating gas ( $\text{AlCl}_3$ ).

[0024] An exemplary outwardly grown platinum modified diffusion aluminide bondcoat pursuant to the invention (des-

ignated MDC-150L) formed on Rene' N5 nickel base superalloy has higher concentrations of Pt and Al and lower concentrations of harmful refractory metal impurities (e.g. Mo, W, Cr, Ta, etc.) at the outermost region (additive layer) of the bondcoat than at the innermost region thereof as illustrated in Figure 1, which is a graph of concentrations, in weight %, of Pt, Al, Cr, W, Ta, and Mo across the thickness of the platinum modified diffusion bondcoat where about 0 microns to 30 microns distance inwardly through the bondcoat corresponds to the outermost additive layer or zone and about 35 microns to about 50 microns inwardly corresponds to an innermost diffusion zone. The outwardly grown platinum modified diffusion aluminide coatings of the type described above and in US Patents 5 658 614 and 5 989 733 are preferred since they include the outermost additive layer or zone that is relatively clean and purified (i.e. having reduced concentrations of refractory metal and surface active impurities) as a result of outward coating growth and purification by gas-solid reactions during CVD coating such that a pure, thermodynamically stable alpha alumina scale or layer can be formed thereon by heat treatment in air without transient oxidation or spinel formation. Since refractory metal impurities in the bondcoat hinder formation of the desired high purity alpha alumina phase on the bondcoat, their reduced concentration in the outermost additive layer helps minimize harmful doping effects that refractory elements may produce when dissolved in the alpha alumina scale. In addition, reduction of surface active impurities improves aluminum adherence to the bondcoat.

[0025] In the outer additive layer of the bondcoat, the Pt and Al concentrations typically are in the ranges of 12 to 30 weight % Pt and 15 and 28 weight % Al, respectively, while being 0 to 8 weight % Pt and 4 to 12 weight % Al, respectively, at the innermost region of the bondcoat adjacent the substrate. The refractory metal impurities, such as Mo, W, Cr, Ta, etc.) typically each are present in an amount less than about 1 weight % for Mo, W, and Ta and less than 3 weight % for Cr in the outermost additive layer, while being present at their respective nominal alloy concentrations in the diffusion zone at the innermost diffusion zone or region adjacent the substrate. The refractory metal impurities in the bondcoat originate from the underlying superalloy substrate via outward diffusion from the substrate.

[0026] For purposes of illustration and not limitation, the exemplary bondcoat chemistry profile shown in Figure 1 was formed on the Pt plated Rene' N5 substrate using the following coating parameters: coating gas comprising 9 volume % aluminum trichloride and 91 volume % hydrogen at a flow rate of 300 scfh and total pressure of 150 torr and substrate temperature of 1975 degrees F for a coating time of 16 hours without prediffusion of a platinum layer thereon. Prior to CVD aluminizing, the substrate was electroplated with the platinum layer comprising 9-11 milligrams/cm<sup>2</sup> of Pt using an alkali or alkaline earth hydroxide plating bath having a bath composition comprising an aqueous KOH solution with 10 grams Pt per liter and electrical current of less than 20 mA/cm<sup>2</sup>, as taught in U.S. Patent 5 788 823 incorporated herein by reference.

[0027] In accordance with an embodiment of the invention, the outwardly grown platinum modified diffusion aluminide bondcoat on the substrate is treated in a manner that reduces grain boundary ridges on the outermost bondcoat surface, while leaving at least a portion and preferably all of the Pt and Al-rich outermost zone or region (outer additive layer), and then to form a stable alpha alumina layer on the bondcoat prior to deposition of the ceramic thermal insulative layer thereon.

[0028] For purposes of illustration and not limitation, the outermost surface of the bondcoat was subjected to different surface treatments comprising media bowl polishing and vapor honing. The outermost surface of the bondcoat also was grit blasted for comparison purposes representative of conventional grit blasting treatment used heretofore to eliminate transient oxide formation on both inwardly and outwardly grown Pt modified diffusion bondcoats and MCrAlY type overlay bondcoats preparatory to deposition of ceramic insulative coating.

[0029] Media bowl polishing of the bondcoat surface pursuant to an embodiment of the invention involved placing the bondcoated substrate in a bowl having commercially available angle cut, cylindrical alumina polishing media of 5/8 X 5/8 inch particle size and vibrating the bowl such that the bondcoat outermost surface was vibratory polished for a time of 5 minutes. Media bowl polishing of the bondcoat was conducted in equipment and using alumina media commercially available from Sweco Inc., Florence, Kentucky. For example, a Sweco model FMD20HA media bowl polishing device operates at a frequency of vibration of 1200 cycles/minute with a vertical amplitude range of 1/8-3/8 inch and horizontal amplitude range of 1/8-1/4 inch. Media bowl polishing repetitively moves the bondcoated substrate and abrasive media in contact in a container (bowl) by vibration of the container.

[0030] Vapor honing of the bondcoat surface involved impinging the bondcoat outermost surface with vapor comprising water and commercially available -600 grit Novaculite particles at a pressure of 30 psi for a time of 5 minutes. Vapor honing of the bondcoat was conducted in equipment commercially available from Vapor Blast Manufacturing Company, Milwaukee, Wisconsin.

[0031] Grit blasting of the bondcoat surface involved impinging the bondcoat outermost surface with abrasive alumina grit particulates having a particle size of 220-240 grit at a pressure of 20 psi for a time of 3/4 minute. Grit blasting of the bondcoat was conducted in equipment commercially available from Empire Abrasive Equipment Company, Langhorne, Pennsylvania.

[0032] After media bowl polishing, the bondcoated substrates were subjected to heat treatment at 1975 degrees F for sufficient time (determined from Figure 8) in air to form a stable thermally grown alpha alumina layer and then

conventionally coated in an electron beam-physical vapor deposition (EB-PVD) coater with yttria stabilized zirconia insulative layer to a thickness of 0.005-0.007 inch (127-178 micrometers). Grit blasted samples received a vacuum heat treatment at 1925 degrees F for 2 hours similar to U.S. Patent 5 716 720 prior to coating. Vapor honed samples were treated with molten KOH to remove embedded Novaculite particles and air heat treated at 1975 degrees F for 3.75 hours prior to coating.

[0033] The heating time in air that is sufficient to form stable alpha alumina on the coating of media bowl polished samples depended on the time of media bowl polishing (i.e. amount of work imparted to the coating surface), Figure 8, where it can be seen that increased media bowl polishing time decreases the time needed to form the stable alpha alumina at 1975 degrees F.

[0034] The thermal barrier coated substrates then were tested in cyclic oxidation in test cycles where each cycle was 60 minutes in duration consisting of exposure to 2075 degrees F for 50 minutes in air followed by 10 minutes of cooling in air to below 400 degrees F. A thermal barrier coated substrate was considered failed when 20% of the thermal barrier coating on the outermost surface was spalled. The cyclic oxidation tests involved testing 3 specimens of each thermal barrier coated substrate with the lives of the specimens averaged and appearing in Figures 2 and 3.

[0035] Figure 2 summarizes the cyclic oxidation test results where it can be seen that the media bowl polishing pursuant to the invention produced the longest coating life of the three bondcoat surface treatments conducted. The significant advantage of the media bowl polishing over the vapor honed and grit blasted bondcoated substrates results from reduction or elimination of raised grain boundary surface ridges on the outermost surface of the bondcoat without removing any of the Pt and Al-rich outermost additive layer or region of the bondcoat as shown in Figure 4B and 4C compared to Figure 4A. That is, the grain boundary ridges are preferentially removed in Figure 4B as evidenced by abrasive scratch marks on the raised ridges and not on the grains enclosed by the grain boundary ridges. In Figure 4C, abrasive scratch marks are present on the grain boundary ridges and some of the grain surfaces, indicating that the ridges are nearly removed level with the grain surfaces at the outer surface of the bondcoat without removing any of the Al and Pt-rich outer additive layer of the bondcoat. Media bowl polishing for 5 minutes improved the life (e.g. 742 cycles) of the thermal barrier coated substrate by 42% in the cyclic oxidation tests as compared to that (e.g. 525 cycles) of similar thermal barrier coated substrate prepared without media bowl polishing; i.e. with no surface treatment except air preoxidation.

[0036] In contrast, vapor honing and grit blasting removed substantial portions of the Pt and Al-rich outermost additive layer or region as shown in Figures 5A, 5B and 6A, 6B in a manner that adversely affected coating life in the cyclic oxidation tests. Both the vapor honing and grit blasting surface treatments failed to produce an improvement in the life of the thermal barrier coated substrate as compared to that of a similar thermal barrier coated substrate prepared with no surface treatment at all. Figures 5 and 6 evidence gross removal [e.g. tenths of a mil (mil = 0.001 inch) of bondcoat removed] of the bondcoating itself to the detriment of oxidation resistance.

[0037] Figure 3 illustrates life of the thermal barrier coated substrates prepared as above using media bowl polishing pursuant to the invention with, however, the time of media bowl polishing being varied. In these cyclic oxidation tests, the media bowl polished bondcoated substrates were heat treated at 1975 degrees F for sufficient time in air, Figure 8, to form a completely transformed alpha alumina layer or scale on the bondcoat before deposition of the yttria stabilized zirconia layer. Although the life of the thermal barrier coated substrates started to decrease with increasing media bowl polishing beyond about 5 minutes, media bowl polishing for about 3 to about 10 minutes significantly improved the life of the thermal barrier coated substrate. Even after 30 minutes of media bowl polishing, the thermal barrier coated substrates still exhibited better life (e.g. about 575 cycles) in the cyclic oxidations tests as compared to that (e.g. 525 cycles) of similar thermal barrier coated substrate prepared without media bowl polishing; i.e. with no surface treatment except air preoxidation.

[0038] Although the invention has been described hereabove with respect to forming an outwardly grown Pt modified diffusion aluminide coating by CVD processing, the invention is not so limited and can be practiced by forming an outwardly grown simple diffusion aluminide coating devoid of Pt on the substrate using CVD processes of the type described above. Also, the outwardly grown diffusion aluminide coatings may include one or more active elements selected from Hf, Zr, Si, Y, La, and Ce with or without platinum and also can be made by CVD, pack, above-the-pack and other vapor phase coating processes.

[0039] The present invention also involves heat treating the pretreated bondcoated substrate under temperature and time conditions in an oxygen-bearing atmosphere to form a thermodynamically stable alpha alumina layer on the bondcoat prior to application of the thermal insulative layer. Rene' N5 substrates coated with the above bondcoat were subjected to various air heat treatments at 1950, 1975, 2000, and 2150 degrees F for various times. The resulting transformation start  $T_s$  and transformation finish  $T_f$  times with respective temperatures for the formation of alpha alumina on the bondcoat are shown in Table I.

Table I

Temperature (degrees F)	Transformation Start ( $T_s$ )	Transformation Finish ( $T_f$ )
1950	1 hour	about 8 hours
1975	30 minutes	less than 1 hour
2000	30 minutes	less than 1 hour
2150	less than 10 minutes	less than 30 minutes

[0040] Table I reveals that a stable alpha alumina layer can be formed on the bondcoat by heat treatment at temperatures of 1950 degrees F and above within approximately 8 hours and less. Higher temperatures considerably reduced the heat treatment time to form the fully transformed alpha alumina layer on the bondcoat.

[0041] The  $T_s$  and  $T_f$  data points were chosen with respect to the time at which the stable alpha alumina phase peaks ( $T_s$ ) were first detected by X-ray diffraction analysis and when the last theta alumina peaks were no longer detectable ( $T_f$ ). From these air heat treatment data points, a time-temperature-transformation (TTT) diagram was developed and is shown in Figure 7. In Figure 7, the 2150 degree F  $T_s$  was extrapolated.

[0042] Further, Rene' N5 substrates coated with the CVD Pt aluminide MDC-150L bondcoats without any bondcoat surface treatment were preoxidized in air at 1975 degrees F for 30 minutes and then examined by X-ray diffraction both prior to and after a standard pre-heat cycle (i.e. 40 minutes at 1950 degrees F in vacuum of 6 microns) employed in the conventional EB-PVD coater in which the yttria stabilized zirconia was deposited on the bondcoat. X-ray diffraction analysis indicated that the transformation from theta alumina to alpha alumina was not complete following preoxidation and did not proceed during the EB-PVD pre-heat operation. These results suggest that the optimum fully transformed alpha alumina layer to maximize life of the thermal barrier coated substrate cannot be formed during the EB-PVD pre-heat cycle, or any other thermal process at reduced oxygen pressure and temperatures at or below 1950 degrees F. Thus, pursuant to a preferred embodiment of the invention, the substrate is heat treated in air at temperatures of about 1950 degrees F and higher for appropriate times to form the alpha alumina layer prior to placing the bondcoated substrate in the EB-PVD coater that is used to deposit the ceramic insulative layer. The bondcoat can be heated in air at a temperature in the range of about 1900, preferably about 1950, to about 2200 degrees F for 1 to 500 minutes to form the alpha alumina layer.

[0043] Although the invention has been described in detail above with respect to certain embodiments, those skilled in the art will appreciate that modifications, changes and the like can be made therein without departing from the spirit and scope of the invention as set forth in the appended claims.

## Claims

1. A method of forming a thermal barrier coating system on a substrate, comprising

forming on said substrate a diffusion aluminide bondcoat that has a higher concentration of Al and a lower concentration of a refractory metal at an outermost region of the bondcoat than at an innermost region thereof, and

repetitively moving the bondcoated substrate and abrasive media in contact to reduce grain boundary ridges on an outermost surface of said bondcoat while leaving at least a portion of said outermost region on said bondcoat.

2. The method of claim 1 wherein said bondcoated substrate is media bowl polished at room temperature.

3. The method of claim 2 wherein said media bowl polishing occurs for about 2 to about 10 minutes.

4. The method of claim 1 further including heating the bondcoated substrate to an elevated temperature for a time in an oxygen-bearing atmosphere to form a stable alpha alumina layer on the bondcoat.

5. The method of claim 4 wherein said bondcoated substrate is heated to at least 1950 degrees F for a time of 8 hours or less.

6. The method of claim 4 further including depositing a ceramic layer on the alpha alumina layer.

7. The method of claim 1 wherein said bondcoat is formed by chemical vapor deposition at a temperature of at least 1832 degrees F.
8. The method of claim 1 wherein an outwardly grown platinum modified diffusion aluminide bondcoat is formed on the substrate and has higher concentrations of Al and Pt and lower concentrations of a refractory metal at an outermost region of the bondcoat than at an innermost region thereof.
9. A method of forming a thermal barrier coating system on a substrate, comprising
  - forming on said substrate a diffusion aluminide bondcoat that has a higher concentration of Al and lower concentration of a refractory metal at an outermost region of the bondcoat than at an innermost region thereof, and
  - heating the bondcoat in air at a temperature of at least 1950 degrees F for sufficient time to form a stable alpha alumina layer on the bondcoat, and
  - depositing a ceramic layer on the alpha alumina layer.
10. The method of claim 9 wherein the bondcoat is heated in air at a temperature in the range of about 1900 to about 2200 degrees F for 1 to 500 minutes.
11. A coated article, comprising a substrate and a diffusion aluminide bondcoat on said substrate, said bondcoat having a higher concentration of Al and lower concentration of a refractory metal at an outermost region of the bondcoat than at an innermost region thereof adjacent to said substrate, said bondcoat having an aluminum-rich outermost region with an outermost surface abraded by repetitive movement in contact with abrasive media to reduce gain boundary ridges on said surface while leaving at least a portion of said outermost region of said bondcoat.
12. The article of claim 11 wherein said bondcoat is media bowl polished.
13. The article of claim 11 wherein the bondcoat also includes Pt and said Pt and Al concentrations are at least 11 and 13 weight % at said outermost region.
14. The article of claim 11 wherein said substrate is nickel base superalloy.
15. The article of claim 11 further including an alpha alumina layer on said bondcoat.
16. The article of claim 15 further including a ceramic layer on the alumina layer.




FIG. 1








FIG. 2




**FIG. 4A**




**MDC-150L As Coated**

**FIG. 4B**




**MDC-150L 10min. Media Bowl**

**FIG. 4C**




**MDC-150L 30min. Media Bowl**




**MDC-150L 20psi Vapor Hone**

**FIG. 5A**




**MDC-150L 60psi Vapor Hone**


**FIG. 5B**



**MDC-150L 20psi Blast**  
**FIG. 6A**



**MDC-150L 40psi Blast**  
**FIG. 6B**






FIG. 8



European Patent  
Office

# EUROPEAN SEARCH REPORT

Application Number  
EP 01 10 2982

DOCUMENTS CONSIDERED TO BE RELEVANT			
Category	Citation of document with indication, where appropriate, of relevant passages	Relevant to claim	CLASSIFICATION OF THE APPLICATION (Int.C1.7)
Y	EP 0 386 386 A (UNITED TECHNOLOGIES CORPORATION) 12 September 1990 (1990-09-12) * claims 1-35 *	1,11,14	C23C28/00 C23C4/02
Y	US 4 321 310 A (NICHOLAS E. ULION) 23 March 1982 (1982-03-23) * column 4, line 17 - line 36; claims 1-5; examples 1,2 *	1,11,14	
A	US 4 897 315 A (DINESH K. GUPTA) 29 July 1975 (1975-07-29) * claims 1-14 *	2,4-7,9, 12,15,16	
A	US 5 403 669 A (BHUPENDRA K. GUPTA) 4 April 1995 (1995-04-04) * claims 1-7 *	1,11,14	
A	WO 96 34130 A (SIEMENS) 31 October 1996 (1996-10-31) * page 1, line 1 - line 4; claims 1-20 *	1,11,14	
A	US 5 856 027 A (KENNETH S. MURPHY) 5 January 1999 (1999-01-05) * claims 1-17 *	1,4-11, 13-16	TECHNICAL FIELDS SEARCHED (Int.C1.7) C23C
A	EP 0 733 723 A (HOWMET CORPORATION) 25 September 1996 (1996-09-25) * page 4, line 5 - line 8; claims 1-17 *	1,4-11, 13-16	
A	EP 0 718 419 A (ROLLS-ROYCE) 26 June 1996 (1996-06-26)		
A	EP 0 587 341 A (ROLLS-ROYCE) 16 March 1994 (1994-03-16)		
A	EP 0 821 078 A (HOWMET RESEARCH CORPORATION) 28 January 1998 (1998-01-28)		
The present search report has been drawn up for all claims			
Place of search THE HAGUE		Date of completion of the search 7 June 2001	Examiner Elsen, D
CATEGORY OF CITED DOCUMENTS X: particularly relevant if taken alone Y: particularly relevant if combined with another document of the same category A: technological background O: non-written disclosure P: intermediate document T: theory or principle underlying the invention E: earlier patent document, but published on, or after the filing date D: document cited in the application L: document cited for other reasons &: member of the same patent family, corresponding document			

EPO FORM 1503 (3.92) (P4/C01)



**ANNEX TO THE EUROPEAN SEARCH REPORT  
ON EUROPEAN PATENT APPLICATION NO.**

EP 01 10 2982

This annex lists the patent family members relating to the patent documents cited in the above-mentioned European search report. The members are as contained in the European Patent Office EDP file on  
The European Patent Office is in no way liable for these particulars which are merely given for the purpose of information.

07-06-2001

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
EP 386386 A	12-09-1990	US 4933239 A	12-06-1990
		AU 626355 B	30-07-1992
		AU 4590389 A	06-09-1990
		BR 8906389 A	21-08-1990
		CA 2006892 A	06-09-1990
		CN 1045425 A,B	19-09-1990
		DE 68921194 D	23-03-1995
		DE 68921194 T	14-06-1995
		IL 92516 A	28-11-1994
		JP 3001161 B	24-01-2000
		JP 3044484 A	26-02-1991
		NZ 231608 A	25-02-1993
		NZ 241006 A	25-02-1993
		ZA 8909398 A	26-09-1990
US 4321310 A	23-03-1982	AU 543682 B	26-04-1985
		AU 6773281 A	07-08-1981
		BE 886974 A	04-05-1981
		BR 8105749 A	24-11-1981
		CA 1167328 A	15-05-1984
		DE 3162618 D	12-07-1984
		EP 0044329 A	27-01-1982
		IL 61877 A	30-09-1984
		IT 1134958 B	20-08-1986
		JP 1018994 B	10-04-1989
		JP 57500292 T	18-02-1982
		KR 8401682 B	15-10-1984
		NO 812999 A	04-09-1981
		NO 156747 B	10-08-1987
		WO 8101983 A	23-07-1981
		US 4405660 A	20-09-1983
		US 4414249 A	08-11-1983
US 4897315 A	30-01-1990	US 4910092 A	20-03-1990
US 5403669 A	04-04-1995	US 5236745 A	17-08-1993
		CA 2076118 A	14-03-1993
		EP 0532255 A	17-03-1993
		JP 5195188 A	03-08-1993
WO 9634130 A	31-10-1996	CZ 9703409 A	17-06-1998
		DE 69603183 D	12-08-1999
		DE 69603183 T	23-03-2000
		DK 826076 T	07-02-2000
		EP 0826076 A	04-03-1998
		ES 2135900 T	01-11-1999

EPO FORM 10469

For more details about this annex : see Official Journal of the European Patent Office, No. 12/82

**ANNEX TO THE EUROPEAN SEARCH REPORT  
ON EUROPEAN PATENT APPLICATION NO.**

EP 01 10 2982

This annex lists the patent family members relating to the patent documents cited in the above-mentioned European search report. The members are as contained in the European Patent Office EDP file on  
The European Patent Office is in no way liable for these particulars which are merely given for the purpose of information.

07-06-2001

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
WO 9634130 A		JP 11504076 T	06-04-1999
US 5856027 A	05-01-1999	US 5716720 A	10-02-1998
		DE 69603108 D	12-08-1999
		DE 69603108 T	20-01-2000
		EP 0733723 A	25-09-1996
		JP 8260128 A	08-10-1996
EP 733723 A	25-09-1996	US 5716720 A	10-02-1998
		DE 69603108 D	12-08-1999
		DE 69603108 T	20-01-2000
		JP 8260128 A	08-10-1996
		US 5856027 A	05-01-1999
EP 718419 A	26-06-1996	AU 695086 B	06-08-1998
		AU 4068595 A	04-07-1996
		AU 695087 B	06-08-1998
		AU 4068695 A	04-07-1996
		CA 2165641 A	25-06-1996
		CA 2165932 A	25-06-1996
		DE 69504023 D	17-09-1998
		DE 69504023 T	10-12-1998
		DE 69509202 D	27-05-1999
		DE 69509202 T	09-09-1999
		EP 0718420 A	26-06-1996
		JP 8225958 A	03-09-1996
		JP 8225959 A	03-09-1996
		NO 955187 A	25-06-1996
		NO 955188 A	25-06-1996
		US 5645893 A	08-07-1997
		US 5667663 A	16-09-1997
		US 5763107 A	09-06-1998
		US 5981091 A	09-11-1999
EP 587341 A	16-03-1994	DE 69301883 D	25-04-1996
		DE 69301883 T	08-08-1996
		JP 6220607 A	09-08-1994
		US 5500252 A	19-03-1996
EP 821078 A	28-01-1998	US 5989733 A	23-11-1999
		JP 10068062 A	10-03-1998

EPO FORM P/US 8

For more details about this annex : see Official Journal of the European Patent Office, No. 12/82